

Pentens® T-100

Water-Based PU bituminous waterproofing membrane

DESCRIPTION

Pentens T-100 is a single component which is newly developed polymer of MMA, natural rubber, and polyurethane combines with the reaction with asphalt and then being modified and further emulsified to form elastic waterproof membrane.

USES

To provide a better water and vapor-proof in complicating application surface compare to membrane-type and ensure better integrity between applied surfaces and waterproofing coating. Areas of application include:

- Floor slabs
- Suspended floors
- Terraces and balconies
- Patios
- Bathrooms
- RC gutters and planter boxes
- Swimming pools
- Water tanks
- Basements and fountains
- Retaining walls

ADVANTAGES

- Ease of application directly from container.
- High elasticity.
- Superb adhesive strength.
- Can apply directly on damp or wet surfaces.
- The softening point will not be further softened due.
- To hot and humid climate in tropical countries.
- Resistant to any bubbling or side osmosis
- Phenomenon even submerge in water for a long time.
- Non-toxic.

SURFACE PREPARATION

All the surfaces must be clean, free from grease, oil, laitance, and remove all the dirt and contaminants, which might affect adhesion. The impurity outside the structure body should be cleaned thoroughly.

Any crack or water leakage area should be pre-treated and reinforced with Pentens Repair System (for more detail, please refer to our Technical Department) before the waterproofing.

For some difficult areas, such as the position of cracks, secondary joint, right angle of wall and the boundary shall be strengthened first with one layer of Pentens T-100.

TECHNICAL & PHYSICAL DATA

Foam	Paste like Emulsion
Color	Dark Brown
Specific Gravity (CNS 6986, CNS 6988)	1.08
Hardness (HS) (CNS 6986, CNS 6988)	35
Tensile Strength (kgf/cm ²) (ASTM D 412)	20.9
Elongation (%) (ASTM D 412)	1128.6
Tensile Strength at 100% Elongation (kgf/cm ²) (ASTM D 412)	3.5
Tear Strength (kgf/cm ²) (CNS 6986, CNS 6988)	11
100% Modulus of Elasticity (kgf/cm ²) (CNS 6986, CNS 6988)	5.5
Water Vapour Transmission of Materials (ASTM E 96)	6.165 grains/ft ² X h x in x Hg
Puncture (kgf) (ASTM E 154)	1.6
Chemical Resistance (10% HCOOH, 60°C, 24 hrs)	No Changes on the Surface of the sample
Shelf Life	1 year when unopened And damaged
Storage Condition	Store in a dry cool place
Packaging	20 KG Pail



MIXING

Generally it is not required but for smoother application, not more than 1kg of clean water can be added into 20kg of Pentens T-100.

When used as a sand mortar, the amount of sand added to Pentens T-100 will determine the plasticity of the mortar and the hardness of the set material.

APPLICATION

Substrate should be primed with a 1:3 mixture of Pentens T-007 and water. Brush on at the approximate rate of 0.3kg/m².

On areas exposed hot drying winds. 2 to 3 thin coats of paint may be more successful than 1 thick coat. For indoor areas, it is recommended that allow approximately 30 minutes or after the primer becomes tacky then apply T-100.

With brush, roller, or spray method apply the first coat of Pentens T-100 on the application surface. The first coat should be applied in one direction only. If possible the second coat should be applied at right angles to the first. Leave to cure for approximately 8 hours before applying second coat.

COVERAGE

- Bathroom and kitchen: 1KG/M² 2 coats.
- Roof, planter box, balcony, water tank and basement: 1.5KG/M² 2 coats.

CURING

For optimum performance, Pentens T-100 should be allowed to cure for 24 hours before the finishing concrete, tiles etc and during this time precautions must be taken in order to prevent damaging to the coating.

NOTE

The best method to assure good penetration of the first coat into the surface is by application with a nap roller. The succeeding coats may be spray or roller applied.

CLEANING

Tools and equipment just can be clean with clean water immediately after use.

SAFETY

Impervious gloves and barrier cream should be used when handling these products. Eye protection should be worn. In case of contact with eyes, wash thoroughly with plenty of water and seek medical advice if symptoms persist. If contact with skin occurs, it must be removed before curing takes place. Wash off with an industrial skin clearer followed by plenty of soap and water. Do not use solvent. Ensure adequate ventilation when using these products.

IMPORTANT NOTES

1. Thoroughly agitate contents before use.
2. Minimum ambient and substrate temperature is 5°C.
3. Never apply more than 1 kg/m² of Pentens T-100 in one single layer.
4. Apply only to clean, sound substrates where surfaces should be well dampened but free of surface water and leaks.

UFON NANO-CHEMICAL CORP.

No.36, Lane 105, Chengfu Rd.,
Sansia Dist., New Taipei City
23743, Taiwan

Tel: +886 2 26682003
Fax: +886 2 26681546

Disclaimer. All representations and recommendations set forth are given in good faith and to the best of our knowledge. However due to varying conditions and applications, the buyer shall conduct its own tests of this product before use. Under no circumstances will the manufacturer be liable for any loss or damages caused by incorrect usages. The sale of this product shall be on terms and conditions set forth on Pentens order acknowledgement.

